

1751-339
GFR/vjm

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Application of)	
)	
Chun Pyo HONG)	
)	
Serial No. Unassigned)	Examiner: Unassigned
)	
Filed: Herewith)	Group Art Unit: Unassigned
)	
)	
)	

For: RHEOFORMING APPARATUS

PRELIMINARY AMENDMENT

Mail Stop: Patent Application
Commissioner for Patents
P.O. Box 1450
Alexandria, VA 22313-1450

Dear Sir:

Please enter the following amendments before calculation of the filing fee and examination of the merits.

IN THE CLAIMS:

Please Amend the claims as follows:

1. (Original) A rheoforming apparatus, comprising:
a first sleeve, an end of which is formed with an outlet vent for releasing slurries;
a second sleeve for receiving molten metals, an end of the second sleeve being
hinge-connected to the other end of the first sleeve at a predetermined angle;

a stirring unit for applying an electromagnetic field to an area of the second sleeve in which the molten metals are present;

a plunger, which is inserted into the other end of the second sleeve to block the other end of the second sleeve for receiving the molten metals and to pressurize the slurries; and

a forming unit, which is connected to the outlet vent of the first sleeve to form products with a predetermined shape using the slurries.

2. (Original) The rheoforming apparatus according to claim 1, wherein the forming unit is an extrusion unit provided with a transfer roller and a cooler.

3. (Original) The rheoforming apparatus according to claim 1, wherein the forming unit is a press-forming unit provided with a press die.

4. (Original) The rheoforming apparatus according to claim 1, further comprising a first temperature control element, which is installed around the first sleeve to adjust the temperature of the slurries pressurized toward the outlet vent.

5. (Currently Amended) The rheoforming apparatus according to ~~any one of claims 1 to 4~~ claim 1, wherein the stirring unit applies the electromagnetic field to the second sleeve prior to loading the molten metals into the second sleeve.

6. (Currently Amended) The rheoforming apparatus according to ~~any one of claims 1 to 4~~ claim 1, wherein the stirring unit applies the electromagnetic field to the second sleeve simultaneously with loading the molten metals into the second sleeve.

7. (Currently Amended) The rheoforming apparatus according to ~~any one of claims 1 to 4~~ claim 1, wherein the stirring unit applies the electromagnetic field to the second sleeve in the middle of loading the molten metals into the second sleeve.

8. (Currently Amended) The rheoforming apparatus according to ~~any one of claims 1 to 4~~ claim 1, wherein the stirring unit applies the electromagnetic field to the second sleeve until the molten metals in the second sleeve have a solid fraction of 0.001-0.7.
9. (Original) The rheoforming apparatus according to claim 8, wherein the stirring unit applies the electromagnetic field to the second sleeve until the molten metals in the second sleeve have a solid fraction of 0.001-0.4.
10. (Original) The rheoforming apparatus according to claim 9, wherein the stirring unit applies the electromagnetic field to the second sleeve until the molten metals in the second sleeve have a solid fraction of 0.001-0.1.
11. (Currently Amended) The rheoforming apparatus according to ~~any one of claims 1 to 4~~ claim 1, wherein the molten metals in the second sleeve is cooled until the molten metals have a solid fraction of 0.1-0.7.
12. (Original) The rheoforming apparatus according to claim 11, further comprising a second temperature control element, which is installed around the second sleeve to cool the molten metals in the second sleeve.
13. (Original) The rheoforming apparatus according to claim 12, wherein the second temperature control element comprises at least one of a cooler and a heater, which are installed around the second sleeve.
14. (Original) The rheoforming apparatus according to claim 12, wherein the second temperature control element cools the molten metals in the second sleeve at a rate of 0.2-5.0 /sec.
15. (Original) The rheoforming apparatus according to claim 14, wherein the second temperature control element cools the molten metals in the second sleeve at a rate of 0.2-2.0 /sec.